



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

Publication number:

**0 382 366  
A2**

12

## EUROPEAN PATENT APPLICATION

21 Application number: 90300646.8

51 Int. Cl.<sup>5</sup>: C08G 77/08, C08G 77/06

22 Date of filing: 22.01.90

30 Priority: 09.02.89 GB 8902937

43 Date of publication of application:  
16.08.90 Bulletin 90/33

64 Designated Contracting States:  
BE CH DE ES FR GB IT LI NL

71 Applicant: Dow Corning Limited  
Inveresk House 1 Aldywch  
London WC2R 0HF(GB)

72 Inventor: Rees, Sian Beverley  
4 Greenwood Drive The Woodlands Llantwit  
Fardre  
Pontypridd Mid Glamorgan Wales(GB)  
Inventor: Westall, Stephen  
41 Meadow Vale Coldbrook  
Barry South Glamorgan Wales(GB)

74 Representative: Walbeoff, William John et al  
Dow Corning Limited Cardiff Road Barry  
South Glamorgan CF6 7YL Wales(GB)

54 Process for the production of organosilicon compounds.

57 A process for the production of an organosilicon condensation product which comprises contacting (A) at least one organosilicon compound having in the molecule at least one silicon-bonded hydroxyl group, the organic substituents being selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with (B) a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides.

EP 0 382 366 A2

## PROCESS FOR THE PRODUCTION OF ORGANOSILICON COMPOUNDS

This invention relates to the production of organosiloxanes and relates in particular to a process for the condensation of organosiloxanes having silicon-bonded hydroxyl groups.

The production of organosiloxane polymers by the polymerisation or copolymerisation of relatively low molecular weight organosiloxanes is a well known step in the manufacture of commercial silicones. Generally the polymerisation or copolymerisation is carried out by contacting cyclic organosiloxanes or low molecular weight siloxanols, or mixtures thereof, with an acidic or a basic equilibration catalyst. Many substances which may be employed as such catalysts have been described in the literature and include sulphuric acid, hydrochloric acid, Lewis acids, sodium hydroxide, potassium hydroxide, tetramethylammonium hydroxide, tetrabutylphosphonium silanolate, amines and others. It is also known from U.S. Patent 3 448 076 that cyanoalkyl-substituted organopolysiloxanes can be equilibrated readily with barium hydroxide even though this reagent is not reactive enough to equilibrate organopolysiloxanes not having cyanoalkyl substituents. However, although equilibration catalysts are effective in producing the desired increase in molecular weight of the starting materials, they cause scission and rearrangement of the siloxane bonds. As a result of such rearrangement the product often contains a significant proportion of low molecular weight siloxanes. For many applications, for example in the fabrication of silicone elastomers, it is necessary to remove such low molecular weight materials by devolatilisation in order to obtain a satisfactory product. Rearrangement of the siloxane bonds is also undesirable when the polymer is to contain a planned distribution of two or more types of organic substituents, for example in the production of a polydimethylsiloxane containing a proportion of organofunctional, e.g. aminoalkyl, substituents.

Catalysts for promoting the reactions  $\equiv\text{SiOH} + \equiv\text{SiOH}$  and  $\equiv\text{SiOH} + \text{SiOR}$ , R = organic, without siloxane bond cleavage have been disclosed in G.B. 895 091 and 918 823 and include for example tetramethylguanidine 2-ethylcaproate and n-hexylamine 2-ethylcaproate. However, many of such catalysts are liquids, or are not suitable for use at high temperatures, or are not readily removable from the product. There has, therefore, been a continuing search for substances which would be effective as catalysts for the production of condensation products of organosiloxanols but which would not cause molecular rearrangement and the consequent presence of significant amounts of low molecular weight species in the product. In particular the desired catalysts should preferably be suitable for use in heterogeneous systems and remain active during use, thereby enabling their recovery and re-use in batch processes or their application in a continuous process.


We have now found that hydroxides of certain metals have the ability to catalyse the condensation of organosilicon compounds. We have further found that said hydroxides can advantageously be employed in the production of organosilicon polymers having a relatively low content of low molecular weight species.

Accordingly, the present invention provides a process for the production of an organosilicon condensation product which comprises contacting (A) at least one organosilicon compound having in the molecule at least one silanol group and wherein the silicon-bonded organic substituents are selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with (B) a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides.

The process of this invention may be applied in the production of condensation products of any type of organosilicon compound having at least one silanol, that is  $\equiv\text{SiOH}$ , group in the molecule. Thus, the organosilicon compound may be an organosilane, organosiloxane or a silcarbane or mixtures of the same type or of different types of such organosilicon compounds. The silicon-bonded organic substituents in the organosilicon compound may be monovalent hydrocarbon groups having from 1 to 14 carbon atoms, for example alkyl, aryl, aralkyl, alkaryl or alkenyl groups or monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms for example amino-substituted alkyl and aryl groups, mercaptoalkyl groups, haloalkyl groups, esterified carboxyalkyl groups and hydroxyalkyl groups. Specific examples of the organic substituents which may be present in the organosilicon compounds employed in the process of this invention are methyl, ethyl, propyl, hexyl, dodecyl, tetradecyl, phenyl, xylyl, tolyl, phenylethyl, vinyl, allyl, hexenyl,  $-\text{RNH}_2$ ,  $-\text{RNHCH}_2\text{CH}_2\text{NH}_2$ ,  $-\text{RSH}$ ,  $-\text{RBr}$ ,  $-\text{RCl}$  and  $-\text{ROH}$  wherein R represents a divalent organic group, preferably having less than 8 carbon atoms for example alkylene e.g.  $-(\text{CH}_2)_3-$  and  $-\text{CH}_2\text{CHCH}_3\text{CH}_2-$ , arylene e.g.  $-\text{C}_6\text{H}_4-$  or aralkylene e.g.  $-(\text{C}_6\text{H}_4.\text{CH}_3)-$ . For the majority of commercial applications at least 50% of the organic substituents will be methyl, any remaining substituents being selected from vinyl and phenyl.

Although applicable to any type of organosilicon compound having at least one silanol group the

process of this invention is particularly useful for the production of higher molecular weight organosiloxane polymers from lower molecular weight hydroxylated species. For example, during the production of organosiloxanes by the hydrolysis of the corresponding organochlorosilanes there is obtained a mixture of low molecular weight organosiloxanes having two or more silanol groups per molecule. The process of this invention may be employed to increase the molecular weight of such organosiloxanes while avoiding the production of undue amounts of volatile siloxanes. According to a preferred embodiment of this invention the organosilicon compounds (A) are silanol-terminated polydiorganosiloxanes, that is substantially linear organosiloxane polymers and oligomers having a hydroxyl group attached to each terminal silicon atom. Such polydiorganosiloxanes include those which can be represented by the average general formula



wherein each R' represents the hereinabove defined organic substituents and n is an integer, preferably from 1 to about 100. Commercially the R' substituents are normally predominantly methyl with any remaining R' substituents being selected from vinyl and phenyl. Said silanol-containing polydiorganosiloxanes are produced when diorganohalosilanes are hydrolysed during the commercial production of silicones. The resulting hydrolysis product is usually subjected to a separation procedure whereby the cyclic siloxanes, which are also formed, are removed by distillation.

If desired the condensation products may be end-stopped with triorganosiloxy units. One method of effecting such end-stopping comprises incorporating a triorganoalkoxy silane in the reaction mixture as hereinafter described. However, a more preferred method of producing end-stopped polydiorganosiloxanes employing the process of this invention comprises employing as organosilicon compound (A) both (i) a silanol-terminated polydiorganosiloxane and (ii) a polydiorganosiloxane terminated with a silanol group at one end and a triorganosiloxy group at the other.

The catalyst substance (B) is any hydroxide of magnesium, calcium, strontium or barium, the preferred substances being strontium hydroxide and barium hydroxide. The compounds may be employed in their anhydrous or hydrated forms. The particle size of the catalyst substance (B) is not critical. Generally, the smaller the particles the greater is the catalytic surface available. However, very fine particle size powders may be more difficult to remove from the condensation product.

The process of this invention involves contacting the organosilicon compound (A) with the catalyst (B) at a temperature at which the desired rate of molecular weight increase occurs. The temperatures employed may vary within wide limits for example from about 30°C to about 200°C. Reaction at the lower temperatures is, however, normally too slow for commercial purposes and the process is preferably carried out at temperatures within the range from about 70°C to 150°C. Preferably also, the removal of water formed during the condensation reaction is accelerated by carrying out the process under reduced pressure, that is, at a pressure less than normal atmospheric and most preferably less than about 0.5 bar.

One method of carrying out the process is by means of a batch procedure. For example, the catalyst may be dispersed in the organosilicon compound and the mixture raised to the required temperature. Alternatively, the organosilicon compound may be preheated prior to the addition of the catalyst. Advantageously the mixture is agitated during the reaction period to maintain the catalyst in suspension. Sufficient catalyst is employed to achieve the desired rate of condensation having regard to the nature and geometry of the processing equipment, temperature and other factors. From considerations of speed of reaction and economy of operation we prefer to employ from about 0.001 to about 5% by weight of the catalyst (B) based on the weight of the organosilicon compound. Termination of the condensation reaction, if desired, may be achieved by for example lowering the temperature of the mixture and/or by raising the reaction pressure to atmospheric and/or by separation or neutralisation of the catalyst. For most applications it is preferred to separate the catalyst from the condensation product on completion of the reaction, for example by filtration.

Because of their heterogeneous nature the catalysts (B) are particularly adapted for use in processes involving manufacture on a continuous, rather than a batch, basis. Properly employed such so-called 'continuous processes' avoid the delays and costs common to batch processing, for example those involved in the charging and discharging of the reaction vessel and separation of the catalyst material from the product. Thus, for example, the process of this invention may be advantageously employed for the

continuous production of higher molecular weight siloxane polymers from lower molecular weight hydroxyl-containing species. When carrying out the process of this invention in a continuous mode contact between the catalyst material and the organosilicon compound may be achieved by passing the organosilicon compound over or through a bed of the catalyst material. When employing viscous reactants or products it may be necessary to adjust the porosity of the bed by granulation of the catalyst or other means. We have found that a particularly suitable form of bed for both continuous and batch operation can be obtained by depositing the catalyst substance in or on an inert particulate solid material, for example silica, having a particle size appropriate to the desired porosity of the bed.

The process of this invention is suitable for use in the preparation of a variety of organosilicon products by a condensation reaction. If desired there may be included with the organosilicon compound (A) other organosilicon compounds for example alkoxysilanes which are reactive with the silanol-containing reactant or condensation product to provide organofunctional or chain-terminating groups. Examples of such alkoxysilanes are  $(\text{CH}_3)_3\text{SiOCH}_3$ ,  $\text{CH}_3\text{C}_6\text{H}_5\text{Si}(\text{OCH}_3)_2$ ,  $\text{C}_6\text{H}_5\text{CH}_3(\text{CH}_2=\text{CH})\text{SiOC}_2\text{H}_5$ ,  $\text{H}_2\text{N}(\text{CH}_2)_3\text{Si}(\text{CH}_3)_2\text{OCH}_3$  and  $\text{H}_2\text{NCH}_2\text{CH}_2\text{NH}(\text{CH}_2)_3\text{Si}(\text{CH}_3)(\text{OC}_2\text{H}_5)_2$ . Catalysts for the reaction  $\equiv\text{SiOH} + \equiv\text{SiOR}$  may be added if desired to expedite the reaction between the alkoxysilane and the silanol-containing organosilicon product. We have, however, found that said reaction is catalysed by strontium hydroxide and barium hydroxide and the addition of other catalyst substances is unnecessary when such hydroxides are present in the reaction mixture.

The condensation products produced by the process of this invention may be employed in any of the variety of applications for the corresponding products made by prior art procedures. For example they find application in the treatment of textiles to render them water repellent and impart softness, as components of paper coating compositions to impart non-stick properties and in the production of adhesives and sealing materials.

The following Examples in which Me represents methyl illustrate the invention.

#### Example 1

To 500g of an  $\alpha,\omega$ -hydroxy polydimethylsiloxane having a number average molecular weight  $M_n$  by g.p.c of 3,300 was added with mixing 10g of  $\text{Mg}(\text{OH})_2$ . The mixture was agitated vigorously and heated to  $100^\circ\text{C}$  for 2 hours under a pressure of 13 mbar. Condensation polymerisation of the polydimethylsiloxane occurred and the water formed was removed by distillation. The reaction mixture was then allowed to cool and the polymeric product examined by gel permeation chromatography.

The experiment was repeated employing respectively  $\text{Ca}(\text{OH})_2$ ,  $\text{Sr}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  and  $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  in place of the  $\text{Mg}(\text{OH})_2$  and in the same proportion (2% by weight).

The values of  $M_n$  obtained in each case were as follows.

Catalyst	$M_n$ of Product
None	3,300
$\text{Mg}(\text{OH})_2$	4,257
$\text{Ca}(\text{OH})_2$	5,313
$\text{Sr}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$	31,416
$\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$	445,500

No detectable quantities of volatile siloxane materials were generated during the experiments.

#### Example 2

Pellets of an amorphous silica were agitated ultrasonically in a saturated aqueous solution of  $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  for 18 hours. The aqueous liquor was then decanted and the pellets allowed to dry in an atmosphere free of  $\text{CO}_2$ .

The treated pellets (5g) were added to 250g of an  $\alpha,\omega$ -hydroxyl polydimethylsiloxane having a viscosity of 79 mPa.s at  $25^\circ\text{C}$  and the mixture heated to  $100^\circ\text{C}$  under 40 mbar pressure for 3 hours with constant agitation. After cooling to room temperature the catalyst was removed by filtration to leave a polydimethyl-

siloxane having a viscosity of 10 Pa.s at 25° C and a silicon-bonded hydroxyl content of 786 ppm. No detectable quantity of volatile siloxane was produced during the reaction.

### 5 Example 3


1,130g of an  $\alpha,\omega$ -hydroxy polydimethylsiloxane ( $M_n = 3000$  by g.p.c analysis), 41.6g of trimethylmethoxysilane and 5.8g of  $Ba(OH)_2 \cdot 8H_2O$  were mixed together and the mixture heated to reflux at 60° C/atmospheric pressure for 4 hours. The pressure in the reaction vessel was then reduced to 6 mbar and the temperature raised to 140° C. These conditions were maintained for a further 5 hours during which time the viscosity of the reaction mixture reached a constant value. The reaction product was then cooled and filtered to yield a trimethylsilyl-terminated polydimethylsiloxane having a viscosity of 263 mPa.s at 25° C and a total hydroxyl content of 142 ppm of which 51 ppm was attributable to silanol groups and the remainder to water. No detectable siloxane volatile materials were generated during the reaction.

15

### Example 4

0.25g of strontium hydroxide octahydrate was added to 250g of an  $\alpha,\omega$  silanol-terminated methylvinylsiloxane of average composition

20



25

where  $n = 8.25$  and initial hydroxyl content of 23,968 ppm OH. The mixture was heated at 105° C and 105 mbar pressure for 2 hours. After this time the hydroxyl content had decreased to 3980 ppm OH and the methylvinylsiloxane showed an increase in molecular weight equivalent to an average value of  $n$  of 51, as measured by gel permeation chromatograph (g.p.c.).

30

### 35 Example 5

A mixture of siloxane oligomers comprising  $Me_3Si(OSiMe_2)_nOH$  and  $HO(SiMe_2O)_nH$  of viscosity  $72 \times 10^{-6} \text{ m}^2/\text{s}$  at 25° C and containing 12,520 ppm silanol and 1% w/w of  $Me_3Si-$  was heated to 105° C at 105 mbar pressure in the presence of 0.05% w/w barium hydroxide octahydrate. Over a period of four hours the silanol content of the mixture decreased to 70 ppm and the viscosity increased to  $708 \times 10^{-6} \text{ m}^2/\text{s}$  at 25° C. Gpc analysis of the polymer indicated that the product contained only 1.07% cyclosiloxanes and had the average composition  $Me_3Si(OSiMe_2)_nOSiMe_3$  where  $n = 185$ .

40

### 45 Example 6

Cylindrical pellets of an amorphous aluminosilicate of typical size 10mm L x 5mm D were coated with a surface layer of  $Ba(OH)_2 \cdot 8H_2O$ . 25g of the coated pellets were added to 1000g of an  $\alpha,\omega$  silanol-terminated polydimethylsiloxane of average structure  $HO(SiMe_2O)_nH$  where  $n = 35$  to 40, viscosity 82 cS at 25° C and volatile content measured at 135° C of 1.5% w/w. The mixture was agitated to maintain the pellets in suspension and heated to 120° C at a pressure of 15 mbar. After 20 minutes the viscosity of the polydimethylsiloxane had increased to 60,000 cS at 25° C with a volatile content, measured at 135° C, of 3.43% w/w. The solid catalyst was separated by filtration, washed with a liquid dimethylsiloxane and re-used in an exact duplication of the first reaction. Results in the second reaction gave a viscosity of 65000 cS at 25° C and a volatile content of 2.75% w/w.

50

55

1. A process for the production of an organosilicon condensation product which comprises contacting (A) at least one organosilicon compound having in the molecule at least one silanol group and wherein the silicon-bonded organic substituents are selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with (B) a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides.

2. A process as claimed in Claim 1 wherein the organosilicon compound (A) is passed over or through a bed containing (B).

3. A process as claimed in Claim 1 wherein the hydroxide (B) is dispersed in the organosilicon compound (A) and is thereafter separated from the organosilicon condensation product.

4. A process as claimed in Claim 3 wherein the hydroxide (B) is employed in an amount of from 0.001 to 5% by weight based on the weight of (A).

5. A process as claimed in any one of the preceding claims wherein (B) is present dispersed in or on a particulate solid which is inert under the reaction conditions.

6. A process as claimed in any one of the preceding claims wherein organosilicon compound (A) is a silanol-terminated polydiorganosiloxane.

7. A process as claimed in any one of the preceding claims wherein (A) and (B) are contacted at a temperature in the range from 70 °C to 150 °C.

8. A process as claimed in any one of the preceding claims wherein the organosilicon compound (A) comprises both (i) a silanol-terminated polydiorganosiloxane and (ii) a polydiorganosiloxane terminated with a silanol group at one end and a triorganosiloxy group at the other.

9. A process as claimed in any one of the preceding claims wherein at least 50% of the total substituents in (A) are methyl and any remaining substituents are selected from phenyl and vinyl.



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



Publication number:

**0 382 366 A3**

12

## EUROPEAN PATENT APPLICATION

21 Application number: 90300646.8

51 Int. Cl.<sup>5</sup>: **C08G 77/08, C08G 77/06**

22 Date of filing: 22.01.90

30 Priority: 09.02.89 GB 8902937

43 Date of publication of application:  
16.08.90 Bulletin 90/33

84 Designated Contracting States:  
**BE CH DE ES FR GB IT LI NL**

88 Date of deferred publication of the search report:  
02.10.91 Bulletin 91/40

71 Applicant: **Dow Corning Limited**  
**Inveresk House 1 Aldywch**  
**London WC2R 0HF(GB)**

72 Inventor: **Rees, Sian Beverley**  
**4 Greenwood Drive The Woodlands Llantwit**  
**Fardre**  
**Pontypridd Mid Glamorgan Wales(GB)**  
Inventor: **Westall, Stephen**  
**41 Meadow Vale Coldbrook**  
**Barry South Glamorgan Wales(GB)**

74 Representative: **Walbeoff, William John et al**  
**Dow Corning Limited Cardiff Road Barry**  
**South Glamorgan CF6 7YL Wales(GB)**

54 **Process for the production of organosilicon compounds.**

57 A process for the production of an organosilicon condensation product which comprises contacting (A) at least one organosilicon compound having in the molecule at least one silicon-bonded hydroxyl group, the organic substituents being selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with (B) a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides.

**EP 0 382 366 A3**



# EUROPEAN SEARCH REPORT

EP 90 30 0646

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 180 527 (RHONE-POULENC) * Claims 1,5,6,9-12; page 3, paragraphs 5,6; page 4, paragraph 1; page 5; page 10, last paragraph; page 11, paragraphs 1,2,4 *	1,3-9	C 08 G 77/08 C 08 G 77/06
X	EP-A-0 023 187 (RHONE-POULENC) * Claims 1,5,7-10; page 2, lines 11-19; page 3, lines 17-20,28-32; page 8, lines 24-26; page 9, lines 1,7-22; page 10, lines 9-12 *	1,4,6,7,9	
X	US-A-3 642 693 (A.L. JASINSKI) * The whole document *	1,4,7,9	
X	EP-A-0 264 336 (RHONE-POULENC) * Claims 1-3,7,8; page 5, lines 18-27; page 6, lines 60,61; example 2 *	1,4,6-9	
X	FR-A-2 540 128 (RHONE-POULENC) * Claims 1-3,5; page 4, lines 5-14; page 7, lines 28-35; page 8, lines 1-6,31-35; page 9, lines 1-3; page 10, lines 5-15; page 14, lines 29-33; examples 1,2 *	1,4,6-9	
A	US-A-3 477 988 (R.L. OSTROZYNSKI) * Claim 1; column 2, paragraphs 7,8; column 9, paragraphs 4,5; examples 12,15 *	1	
A	FR-A-1 588 200 (NAUCHNO-ISSLEDOVATELSKY INSTITUT SINTETICHESKOGO KAUCHUKA IMENI AKADEMIKA S.V. LEBEDEVVA) * Claim 1; page 1, right-hand column, lines 15-23; examples 11,12 *	1	
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of search 02 July 91	Examiner KANETAKIS I.
<div>CATEGORY OF CITED DOCUMENTS</div> <div>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention</div> <div>E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &amp;: member of the same patent family, corresponding document</div>			





Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) Publication number:

**0 382 366 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **02.11.94** (51) Int. Cl.<sup>5</sup>: **C08G 77/08, C08G 77/06**

(21) Application number: **90300646.8**

(22) Date of filing: **22.01.90**

(54) **Process for the production of organosilicon compounds.**

(30) Priority: **09.02.89 GB 8902937**

(43) Date of publication of application:  
**16.08.90 Bulletin 90/33**

(45) Publication of the grant of the patent:  
**02.11.94 Bulletin 94/44**

(84) Designated Contracting States:  
**BE CH DE ES FR GB IT LI NL**

(56) References cited:  
**EP-A- 0 023 187      EP-A- 0 180 527**  
**EP-A- 0 264 336      FR-A- 1 588 200**  
**FR-A- 2 540 128      US-A- 3 477 988**  
**US-A- 3 642 693**

(73) Proprietor: **Dow Corning Limited**  
**Barry Plant**  
**Cardiff Road**  
**Barry South Glamorgan CF63 2YL Wales**  
**(GB)**

(72) Inventor: **Rees, Sian Beverley**  
**4 Greenwood Drive The Woodlands Llantwit**  
**Fardre**  
**Pontypridd Mid Glamorgan Wales (GB)**  
Inventor: **Westall, Stephen**  
**41 Meadow Vale Coldbrook**  
**Barry South Glamorgan Wales (GB)**

(74) Representative: **Bullows, Michael et al**  
**Dow Corning Limited,**  
**Cardiff Road**  
**Barry, South Glamorgan CF63 2YL, Wales**  
**(GB)**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

## Description

This invention relates to the production of organosiloxanes and relates in particular to a process for the condensation of organosiloxanes having silicon-bonded hydroxyl groups.

5 The production of organosiloxane polymers by the polymerisation or copolymerisation of relatively low molecular weight organosiloxanes is a well known step in the manufacture of commercial silicones. Generally the polymerisation or copolymerisation is carried out by contacting cyclic organosiloxanes or low molecular weight siloxanols, or mixtures thereof, with an acidic or a basic equilibration catalyst. Many substances which may be employed as such catalysts have been described in the literature and include  
 10 sulphuric acid, hydrochloric acid, Lewis acids, sodium hydroxide, potassium hydroxide, tetramethylammonium hydroxide, tetrabutylphosphonium silanolate, amines and others. It is also known from U.S. Patent 3 448 076 that cyanoalkyl-substituted organopolysiloxanes can be equilibrated readily with barium hydroxide even though this reagent is not reactive enough to equilibrate organopolysiloxanes not having cyanoalkyl substituents. However, although equilibration catalysts are effective in producing the desired increase in  
 15 molecular weight of the starting materials, they cause scission and rearrangement of the siloxane bonds. As a result of such rearrangement the product often contains a significant proportion of low molecular weight siloxanes. For many applications, for example in the fabrication of silicone elastomers, it is necessary to remove such low molecular weight materials by devolatilisation in order to obtain a satisfactory product. Rearrangement of the siloxane bonds is also undesirable when the polymer is to contain a planned  
 20 distribution of two or more types of organic substituents, for example in the production of a polydimethylsiloxane containing a proportion of organofunctional, e.g. aminoalkyl, substituents.

EP-A-0 180 527 discloses a process for the poly-condensation of organopolysiloxanes having hydroxysiloxy groups characterised in that there is used as a catalyst a catalytic system comprising (a) at least one alkali metal or alkaline earth metal M in the form of metallic powder or in ionic form and (b) a defined  
 25 nitrogen containing complexing agent for M. The preferred metal is potassium as potassium hydroxide or potassium silanolate.

U.S. Patent 3,642,693 discloses a method of controlling the hydrolysis of an organic trialkoxysilane monomer or mixtures thereof by employing a Group II A metal - containing hydrolysis catalyst such as barium hydroxide, calcium hydroxide or strontium hydroxide. The prepolymer products of the method are  
 30 curable at elevated temperatures to thermoset organopolysiloxanes.

Catalysts for promoting the reactions  $\equiv\text{SiOH} + \equiv\text{SiOH}$  and  $\equiv\text{SiOH} + \equiv\text{SiOR}$ , R = organic, without siloxane bond cleavage have been disclosed in G.B. 895 091 and 918 823 and include for example tetramethylguanidine 2-ethylcaproate and n-hexylamine 2-ethylcaproate. However, many of such catalysts are liquids, or are not suitable for use at high temperatures, or are not readily removable from the product.  
 35 There has, therefore, been a continuing search for substances which would be effective as catalysts for the production of condensation products of organosiloxanols but which would not cause molecular rearrangement and the consequent presence of significant amounts of low molecular weight species in the product. In particular the desired catalysts should preferably be suitable for use in heterogeneous systems and remain active during use, thereby enabling their recovery and re-use in batch processes or their application  
 40 in a continuous process.


We have now found that hydroxides of certain metals have the ability to catalyse the condensation of organosilicon compounds. We have further found that said hydroxides can advantageously be employed in the production of organosilicon polymers having a relatively low content of low molecular weight species.

Accordingly, the present invention provides a process for increasing the molecular weight of organosiloxanes having silicon-bonded hydroxyl groups by condensation polymerisation thereof which comprises contacting (A) at least one substantially linear organosiloxane polymer having terminal silanol groups and wherein the silicon-bonded organic substituents are selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with a catalyst (B) which is a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides wherein the catalyst (B) is dispersed in the organosiloxane polymer (A) and is thereafter separated from the organosiloxane condensation product, or the organosiloxane polymer (A) is passed over or through a bed containing catalyst (B), and wherein catalyst (B) is the sole catalyst for the condensation polymerisation reaction.  
 45

55 The process of this invention is employed in the production of condensation products of linear organosiloxane polymers having a hydroxyl group directly attached to each terminal silicon atom in the molecule. The silicon-bonded organic substituents in the organosiloxane polymers (which term includes oligomers) may be monovalent hydrocarbon groups having from 1 to 14 carbon atoms, for example alkyl,

aryl, aralkyl, alkaryl or alkenyl groups or monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms for example amino-substituted alkyl and aryl groups, mercaptoalkyl groups, haloalkyl groups, esterified carboxyalkyl groups and hydroxyalkyl groups. Specific examples of the organic substituents which may be present in the organosiloxane polymers employed in the process of this invention are methyl, ethyl, propyl, hexyl, dodecyl, tetradecyl, phenyl, xylyl, tolyl, phenylethyl, vinyl, allyl, hexenyl, -RNH<sub>2</sub>, -RNHCH<sub>2</sub>CH<sub>2</sub>NH<sub>2</sub>, -RSH, -RBr, -RCI and -ROH wherein R represents a divalent organic group, preferably having less than 8 carbon atoms for example alkylene e.g. -(CH<sub>2</sub>)<sub>3</sub>- and -CH<sub>2</sub>CHCH<sub>3</sub>CH<sub>2</sub>-, arylene e.g. -C<sub>6</sub>H<sub>4</sub>- or aralkylene e.g. -(C<sub>6</sub>H<sub>4</sub>.CH<sub>3</sub>)-. For the majority of commercial applications at least 50% of the organic substituents will be methyl, any remaining substituents being selected from vinyl and phenyl.

The process of this invention is particularly useful for the commercial production of higher molecular weight organosiloxane polymers from low molecular weight linear hydroxylated species. For example, during the production of organosiloxanes by the hydrolysis of the corresponding organochlorosilanes there is obtained a mixture of low molecular weight organosiloxanes having two silanol groups per molecule. The process of this invention may be employed to increase the molecular weight of such organosiloxanes while avoiding the production of undue amounts of volatile siloxanes. According to a preferred embodiment of this invention therefore the organosiloxane polymers (A) are silanol-terminated polydiorganosiloxanes, which are represented by the average general formula



wherein each R' represents the hereinabove defined organic substituents and n is an integer of from 1 to 100. Commercially the R' substituents are normally predominantly methyl with any remaining R' substituents being selected from vinyl and phenyl. Said silanol-containing polydiorganosiloxanes are produced when diorganohalosilanes are hydrolysed during the commercial production of silicones. The resulting hydrolysis product is usually subjected to a separation procedure whereby the cyclic siloxanes, which are also formed, are removed by distillation.

If desired the condensation products may be end-stopped with triorganosiloxy units. One method of effecting such end-stopping comprises incorporating a triorganoalkoxy silane in the reaction mixture as hereinafter described. However, a more preferred method of producing end-stopped polydiorganosiloxanes employing the process of this invention comprises including in the reaction mixture with (A) a polydiorganosiloxane which has a silanol group at one end of the molecule and a triorganosiloxy group at the other.

The catalyst substance (B) is any hydroxide of magnesium, calcium, strontium or barium, the preferred substances being strontium hydroxide and barium hydroxide. The compounds may be employed in their anhydrous or hydrated forms. The particle size of the catalyst substance (B) is not critical. Generally, the smaller the particles the greater is the catalytic surface available. However, very fine particle size powders may be more difficult to remove from the condensation product.

The process of this invention includes contacting the organosiloxane polymer (A) with the catalyst (B) at a temperature at which the desired rate of molecular weight increase occurs. The temperatures employed may vary within wide limits for example from about 30°C to about 200°C. Reaction at the lower temperatures is, however, normally too slow for commercial purposes and the process is preferably carried out at temperatures within the range from about 70°C to 150°C. Preferably also, the removal of water formed during the condensation reaction is accelerated by carrying out the process under reduced pressure, that is, at a pressure less than normal atmospheric and most preferably less than about 0.5 x 10<sup>5</sup> Pa (0.5 bar).

One method of carrying out the process is by means of a batch procedure. For example, the catalyst may be dispersed in the organosiloxane polymer and the mixture raised to the required temperature. Alternatively, the organosiloxane polymer may be preheated prior to the addition of the catalyst. Advantageously the mixture is agitated during the reaction period to maintain the catalyst in suspension. Sufficient catalyst is employed to achieve the desired rate of condensation having regard to the nature and geometry of the processing equipment, temperature and other factors. From considerations of speed of reaction and economy of operation we prefer to employ from about 0.001 to about 5% by weight of the catalyst (B) based on the weight of the organosiloxane polymer. Termination of the condensation reaction, if desired, may be achieved by for example lowering the temperature of the mixture and/or by raising the reaction pressure to atmospheric and/or by separation or neutralisation of the catalyst. On completion of the reaction

the catalyst is separated from the condensation product for example by filtration.

Because of their heterogeneous nature the catalysts (B) are particularly adapted for use in processes involving manufacture on a continuous, rather than a batch, basis. Properly employed such so-called 'continuous processes' avoid the delays and costs common to batch processing, for example those involved in the charging and discharging of the reaction vessel and separation of the catalyst material from its admixture with the product. Thus, for example, the process of this invention may be advantageously employed for the continuous production of higher molecular weight siloxane polymers from lower molecular weight hydroxyl-containing species. When carrying out the process of this invention in a continuous mode contact between the catalyst material and the organosiloxane polymer may be achieved by passing the organosiloxane polymer over or through a bed of the catalyst material. When employing viscous reactants or products it may be necessary to adjust the porosity of the bed by granulation of the catalyst or other means. We have found that a particularly suitable form of bed for both continuous and batch operation can be obtained by depositing the catalyst substance in or on an inert particulate solid material, for example silica, having a particle size appropriate to the desired porosity of the bed.

The process of this invention is suitable for use in the preparation of a variety of organosiloxane products by a condensation reaction. If desired there may be included with the organosiloxane polymer (A) other organosilicon compounds for example alkoxysilanes which are reactive with the silanol-containing reactant or condensation product to provide organofunctional or chain-terminating groups. Examples of such alkoxysilanes are  $(\text{CH}_3)_3\text{SiOCH}_3$ ,  $\text{CH}_3\text{C}_6\text{H}_5\text{Si}(\text{OCH}_3)_2$ ,  $\text{C}_6\text{H}_5\text{CH}_3(\text{CH}_2=\text{CH})\text{SiOC}_2\text{H}_5$ ,  $\text{H}_2\text{N}(\text{CH}_2)_3\text{Si}(\text{CH}_3)_2\text{OCH}_3$  and  $\text{H}_2\text{NCH}_2\text{CH}_2\text{NH}(\text{CH}_2)_3\text{Si}(\text{CH}_3)(\text{OC}_2\text{H}_5)_2$ . Catalysts for the reaction  $\equiv\text{SiOH} + \equiv\text{SiOR}$  may be added if desired to expedite the reaction between the alkoxysilane and the silanol-containing organosilicon product. We have, however, found that said reaction is catalysed by strontium hydroxide and barium hydroxide and the addition of other catalyst substances is unnecessary when such hydroxides are present in the reaction mixture.

The condensation products produced by the process of this invention may be employed in any of the variety of applications for the corresponding products made by prior art procedures. For example they find application in the treatment of textiles to render them water repellent and impart softness, as components of paper coating compositions to impart non-stick properties and in the production of adhesives and sealing materials.

The following Examples in which Me represents methyl illustrate the invention.

#### Example 1

To 500g of an  $\alpha,\omega$ -hydroxy polydimethylsiloxane having a number average molecular weight Mn by g.p.c of 3,300 was added with mixing 10g of  $\text{Mg}(\text{OH})_2$ . The mixture was agitated vigorously and heated to  $100^\circ\text{C}$  for 2 hours under a pressure of 13 mbar. Condensation polymerisation of the polydimethylsiloxane occurred and the water formed was removed by distillation. The reaction mixture was then allowed to cool and the polymeric product examined by gel permeation chromatography.

The experiment was repeated employing respectively  $\text{Ca}(\text{OH})_2$ ,  $\text{Sr}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  and  $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  in place of the  $\text{Mg}(\text{OH})_2$  and in the same proportion (2% by weight).

The values of Mn obtained in each case were as follows.

Catalyst	Mn of Product
None	3,300
$\text{Mg}(\text{OH})_2$	4,257
$\text{Ca}(\text{OH})_2$	5,313
$\text{Sr}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$	31,416
$\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$	445,500

No detectable quantities of volatile siloxane materials were generated during the experiments.

#### Example 2

Pellets of an amorphous silica were agitated ultra-sonically in a saturated aqueous solution of  $\text{Ba}(\text{OH})_2 \cdot 8\text{H}_2\text{O}$  for 18 hours. The aqueous liquor was then decanted and the pellets allowed to dry in an atmosphere free of  $\text{CO}_2$ .


The treated pellets (5g) were added to 250g of an  $\alpha,\omega$ -hydroxyl polydimethylsiloxane having a viscosity of 79 mPa.s at 25 °C and the mixture heated to 100 °C under 40 mbar pressure for 3 hours with constant agitation. After cooling to room temperature the catalyst was removed by filtration to leave a polydimethylsiloxane having a viscosity of 10 Pa.s at 25 °C and a silicon-bonded hydroxyl content of 786 ppm. No detectable quantity of volatile siloxane was produced during the reaction.

### Example 3

1,130g of an  $\alpha,\omega$ -hydroxy polydimethylsiloxane ( $M_n = 3000$  by g.p.c analysis), 41.6g of trimethylmethoxysilane and 5.8g of  $Ba(OH)_2 \cdot 8H_2O$  were mixed together and the mixture heated to reflux at 60 °C/atmospheric pressure for 4 hours. The pressure in the reaction vessel was then reduced to 6 mbar and the temperature raised to 140 °C. These conditions were maintained for a further 5 hours during which time the viscosity of the reaction mixture reached a constant value. The reaction product was then cooled and filtered to yield a trimethylsilyl-terminated polydimethylsiloxane having a viscosity of 263 mPa.s at 25 °C and a total hydroxyl content of 142 ppm of which 51 ppm was attributable to silanol groups and the remainder to water. No detectable siloxane volatile materials were generated during the reaction.

### Example 4

0.25g of strontium hydroxide octahydrate was added to 250g of an  $\alpha,\omega$  silanol-terminated methylvinylsiloxane of average composition



where  $n = 8.25$  and initial hydroxyl content of 23,968 ppm OH. The mixture was heated at 105 °C and 105 mbar pressure for 2 hours. After this time the hydroxyl content had decreased to 3980 ppm OH and the methylvinylsiloxane showed an increase in molecular weight equivalent to an average value of  $n$  of 51, as measured by gel permeation chromatograph (g.p.c.).

### Example 5

A mixture of siloxane oligomers comprising  $Me_3Si(OSiMe_2)_nOH$  and  $HO(SiMe_2O)_nH$  of viscosity  $72 \times 10^{-6} \text{ m}^2/\text{s}$  at 25 °C and containing 12,520 ppm silanol and 1% w/w of  $Me_3Si-$  was heated to 105 °C at 105 mbar pressure in the presence of 0.05% w/w barium hydroxide octahydrate. Over a period of four hours the silanol content of the mixture decreased to 70 ppm and the viscosity increased to  $708 \times 10^{-6} \text{ m}^2/\text{s}$  at 25 °C. Gpc analysis of the polymer indicated that the product contained only 1.07% cyclosiloxanes and had the average composition  $Me_3Si(OSiMe_2)_nOSiMe_3$  where  $n = 185$ .

### Example 6

Cylindrical pellets of an amorphous aluminosilicate of typical size 10mm L x 5mm D were coated with a surface layer of  $Ba(OH)_2 \cdot 8H_2O$ . 25g of the coated pellets were added to 1000g of an  $\alpha,\omega$  silanol-terminated polydimethylsiloxane of average structure  $HO(SiMe_2O)_nH$  where  $n = 35$  to 40, viscosity 82 cS at 25 °C and volatile content measured at 135 °C of 1.5% w/w. The mixture was agitated to maintain the pellets in suspension and heated to 120 °C at a pressure of 15 mbar. After 20 minutes the viscosity of the polydimethylsiloxane had increased to 60,000 cS at 25 °C with a volatile content, measured at 135 °C, of 3.43% w/w. The solid catalyst was separated by filtration, washed with a liquid dimethylsiloxane and re-used in an exact duplication of the first reaction. Results in the second reaction gave a viscosity of 65000 cS at 25 °C and a volatile content of 2.75% w/w.

## Claims

1. A process for increasing the molecular weight of organosiloxanes having silicon-bonded hydroxyl groups by condensation polymerisation thereof which comprises contacting (A) at least one substantially linear organosiloxane polymer having terminal silanol groups and wherein the silicon-bonded organic substituents are selected from monovalent hydrocarbon groups having from 1 to 14 carbon atoms and monovalent substituted hydrocarbon groups having from 1 to 10 carbon atoms in which the substituents are selected from amino, halogen, mercapto, hydroxyl, amido and ester, with a catalyst (B) which is a hydroxide selected from the group consisting of magnesium, calcium, strontium and barium hydroxides wherein the catalyst (B) is dispersed in the organosiloxane polymer (A) and is thereafter separated from the organosiloxane condensation product, or the organosiloxane polymer (A) is passed over or through a bed containing catalyst (B), and wherein the catalyst (B) is the sole catalyst for the condensation polymerisation reaction.
2. A process as claimed in Claim 1 wherein the catalyst (B) is dispersed in (A) and is employed in an amount of from 0.001 to 5% by weight based on the weight of (A).
3. A process as claimed in Claim 1 or Claim 2 wherein (B) is dispersed in or on a particulate solid which is inert under the reaction conditions.
4. A process as claimed in any one of the preceding claims wherein (A) and (B) are contacted at a temperature in the range from 70 °C to 150 °C.
5. A process as claimed in any one of the preceding claims wherein the organosiloxane polymer (A) is employed in admixture with a polydiorganosiloxane terminated with a silanol group at one end and a triorganosiloxy group at the other.
6. A process as claimed in any one of the preceding claims wherein at least 50% of the total substituents in (A) are methyl and any remaining substituents are selected from phenyl and vinyl.

## Patentansprüche

1. Verfahren zur Erhöhung des Molekulargewichts von Organosiloxanen mit siliciumgebundenen Hydroxylgruppen durch Kondensationspolymerisation, umfassend, daß man (A) mindestens ein im wesentlichen lineares Organosiloxanpolymer mit endständigen Silanolgruppen, worin die siliciumgebundenen organischen Substituenten ausgewählt sind aus monovalenten Kohlenwasserstoffgruppen mit 1 bis 14 Kohlenstoffatomen und monovalenten substituierten Kohlenwasserstoffgruppen mit 1 bis 10 Kohlenstoffatomen, wobei die Substituenten ausgewählt sind aus Amino-, Halogen-, Mercapto-, Hydroxyl-, Amido- und Estergruppen, mit einem Katalysator (B), der ein Hydroxid ausgewählt aus der Gruppe bestehend aus Magnesium-, Calcium-, Strontium- und Bariumhydroxiden ist, in Kontakt bringt, wobei der Katalysator (B) in dem Organosiloxanpolymer (A) dispergiert ist und danach von dem Organosiloxankondensationsprodukt abgetrennt wird oder das Organosiloxanpolymer (A) über oder durch ein den Katalysator (B) enthaltendes Bett geleitet wird, und wobei der Katalysator (B) der einzige Katalysator für die Kondensationspolymerisationsreaktion ist.
2. Verfahren nach Anspruch 1, worin der Katalysator (B) in (A) dispergiert ist und in einer Menge von 0,001 bis 5 Gew.-% bezogen auf das Gewicht von (A) angewendet wird.
3. Verfahren nach Anspruch 1 oder 2, worin (B) in oder auf einem teilchenförmigen Feststoff dispergiert ist, der unter den Reaktionsbedingungen inert ist.
4. Verfahren nach einem der vorhergehenden Ansprüche, worin (A) und (B) bei einer Temperatur im Bereich von 70 °C bis 150 °C in Kontakt gebracht werden.
5. Verfahren nach einem der vorhergehenden Ansprüche, worin das Organosiloxanpolymer (A) in Mischung mit einem Polydiorganosiloxan, das an einem Ende eine Silanolgruppe und an dem anderen Ende eine Triorganosiloxygruppe trägt, angewendet wird.

6. Verfahren nach einem der vorhergehenden Ansprüche, worin mindestens 50% aller Substituenten in (A) Methylgruppen sind und alle verbleibenden Substituenten ausgewählt sind aus Phenyl- und Vinylgruppen.

## 5 Revendications

1. Procédé pour augmenter le poids moléculaire d'organosiloxanes ayant des groupes hydroxyle liés au silicium par une polymérisation par condensation de ceux-ci, qui consiste à mettre en contact (A) au moins un polymère d'organosiloxane essentiellement linéaire ayant des groupes silanol terminaux et dans lequel les substituants organiques liés au silicium sont choisis parmi les groupes d'hydrocarbures monovalents ayant de 1 à 14 atomes de carbone et les groupes d'hydrocarbures monovalents substitués ayant de 1 à 10 atomes de carbone, dans lesquels les substituants sont choisis parmi les groupes amino, halogène, mercapto, hydroxyle, amido et ester, avec un catalyseur (B) qui est un hydroxyde choisi dans le groupe constitué des hydroxydes de magnésium, de calcium, de strontium et de baryum, dans lequel le catalyseur (B) est dispersé dans l'organosiloxane polymère (A) et est ensuite séparé du produit de condensation de l'organosiloxane, ou l'organosiloxane polymère (A) est amené sur ou à travers un lit contenant un catalyseur (B) et dans lequel le catalyseur (B) est le seul catalyseur pour la réaction de polymérisation par condensation.
2. Procédé selon la revendication 1, dans lequel le catalyseur (B) est dispersé dans (A) et est utilisé en quantité de 0,001 à 5% en poids rapportée au poids de (A).
3. Procédé selon la revendication 1 ou 2, dans lequel (B) est dispersé dans ou sur un solide en particules qui est inerte dans les conditions de réaction.
4. Procédé selon l'une quelconque des revendications précédentes, dans lequel (A) et (B) sont mis en contact à une température dans l'intervalle de 70 °C à 150 °C.
5. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'organosiloxane polymère (A) est utilisé en mélange avec un polydiorganosiloxane terminé par un groupe silanol à une extrémité et par un groupe triorganosiloxy à l'autre extrémité.
6. Procédé selon l'une quelconque des revendications précédentes, dans lequel au moins 50% du total des substituants dans (A) sont des groupes méthyle tandis que les substituants restants sont choisis parmi les groupes phényle et vinyle.